

Coating Thickness


INTRODUCTION

Hot dipped zinc coatings and electrozinc coatings both protect steel in a similar manner. The main difference is that hot-dipped zinc coatings are usually thicker and therefore offer a longer life under the same exposure conditions.

The protective life of a metallic zinc coating is essentially a function of the coating thickness. Figure 1 indicates the life to first maintenance for hot-dipped zinc coatings produced on a continuous galvanizing process. This figure is calculated using the zinc corrosion rates from ISO 9223¹ to estimate the life to first maintenance for a variety of different corrosivity categories. This methodology is adopted from Table 2 of ISO 14713-1:2009².

In general for a particular environment the life of a galvanized coating is directly proportional to the zinc coating mass. Similarly, a specific life to first maintenance necessitates increasing zinc coating thickness as the corrosion severity of the environment is increased from C1 to C5.

Figure 1: Life to first maintenance as a function of zinc coating mass and equivalent zinc coating thickness, and corresponding corrosivity categories.



Note¹:

ISO 9223:2012 Corrosion of metals and alloys – Corrosivity of atmospheres – Classification, determination and estimation

Note²:

ISO 14713-1:2009 Zinc coatings – Guidelines and recommendations for the protection against corrosion of iron and steel in structures – Part 1: General principles of design and corrosion resistance

If you have any questions regarding this Bulletin, please contact BlueScope Steel Direct on 1800 800 789.

To ensure you have the most current Technical Bulletin, please go to bluescopesteel.com.au



The information and advice contained in this Technical Bulletin ('Bulletin') is of a general nature only and has not been prepared with your specific needs in mind. You should always obtain specialist advice to ensure that the materials, approach and techniques referred to in this Bulletin meet your specific requirements.



BlueScope Steel Limited makes no warranty as to the accuracy, completeness or reliability of any estimates, opinions or other information contained in this Bulletin and to the maximum extent permitted by law, BlueScope Steel Limited disclaims all liability and responsibility for any loss or damage, direct or indirect, which may be suffered by any person acting in reliance on anything contained in or omitted from this Bulletin.

COLORBOND®, ZINCALUME® and BlueScope are registered trade marks of BlueScope Steel Limited.

© 2015 BlueScope Steel Limited ABN 16 000 011 058. BlueScope Steel (AIS) Pty Ltd ABN 19 000 019 625. All rights reserved.