

# POSSIBLE PROBLEMS RELATED TO THE MIXING OF DIFFERENT PREPAINTED PRODUCTS

## TECHNICAL BULLETIN TB-23

Rev 4, November 2003  
This issue supersedes all previous issues

A common misconception concerning paint is that if two coatings start out the same colour, then these two coatings will be of equivalent colour throughout their service lives. Unfortunately, this is not generally the case and the purpose of this Technical Bulletin is to discuss some of the potential problems associated particularly with mixing BlueScope COLORBOND® prepainted steel with the 'same-colour' prepainted product from other sources. All of these problems relate to the development of a 'differential appearance' over time when painted products are mixed on a single installation. It should be noted that colour difference does not have to be large to be noticeable and may be quite objectionable.

### DIFFERENT PAINT SYSTEMS

1. A major cause of differential appearance is the use of different pigments in two paint systems of the same colour. Close matches to a colour are often achieved with a variety of combinations of pigments and these different combinations may weather to quite different colours.
2. Another source of differential appearance is the fact that the basic organic resins used in different paint formulations will not be identical and will therefore impart different durabilities and properties. The difference in organic resin can lead to two problems:
  - a) coatings having different durability will show different performance in terms of gloss and colour retention and the onset of chalking. These differences will probably result in differential

discolouration, which can occur rapidly or may only be apparent after long-term exposure; and

- b) in some tropical areas, eg South-East Asia, the different properties of the organic resins, particularly their performance at elevated ambient temperatures, may give rise to differential darkening or tropical discolouration. This effect is related to dirt retention and it can appear very rapidly.

It is therefore particularly important that COLORBOND® prepainted steel should not be mixed with another prepainted steel supplier's product on the same installation. At some stage the colours of the different products will diverge and differential appearance will result. The use of an alternative product with possibly inferior durability will naturally exacerbate the problem. Rectification of differential appearance is a costly procedure and will at least involve overpainting the entire installation.

### STOCK TURNOVER

Care should also be taken if it is intended to use old COLORBOND® prepainted steel stock of the same colour as new stock. This is because the paint formulations used may have changed as part of the continuous COLORBOND® prepainted steel performance improvement programme.

If in doubt, please contact the nearest BlueScope Steel Limited Sales Office for technical advice. Brand details of the material in question will greatly assist in providing a prompt response.

The information and advice contained in this Bulletin is of a general nature only, and has not been prepared with your specific needs in mind. You should always obtain specialist advice to ensure that the materials, approach and techniques referred to in this Bulletin meet your specific requirements.

BlueScope Steel Limited makes no warranty as to the accuracy, completeness or reliability of any estimates, opinions or other information contained in this Bulletin, and to the maximum extent permitted by law, BlueScope Steel Limited disclaims all liability and responsibility for any loss or damage, direct or indirect, which may be suffered by any person acting in reliance on anything contained in or omitted from this document.

COLORBOND® is a registered trade mark of BlueScope Steel Limited.  
BlueScope is a trade mark of BlueScope Steel Limited.

*Please ensure you have the current Technical Bulletin as displayed at [www.bluescopesteel.com.au](http://www.bluescopesteel.com.au)*

### BlueScope Steel

Copyright© 2003 BlueScope Steel Limited  
BlueScope Steel Limited ABN 16 000 011 058  
BlueScope Steel (AIS) Pty Ltd ABN 19 000 019 625



AUSTRALIA	SYDNEY	Telephone: (02) 9795 6700
	MELBOURNE	Telephone: (03) 9586 2222
	BRISBANE	Telephone: (07) 3845 9300
	ADELAIDE	Telephone: (08) 8243 7333
	PERTH	Telephone: (08) 9330 0666

OVERSEAS	BlueScope Steel (Malaysia) Sdn Bhd	Telephone: (603) 3250 8333
	BlueScope Steel (Thailand) Limited	Telephone: (66 38) 685 710
	PT BlueScope Steel Indonesia	Telephone: (62 21) 570 7564
	BlueScope Steel Southern Africa (Pty) Limited	Telephone: (27 21) 555 4265