

Product

ZINCALUME® G300 steel is a hot-dipped Al-Zn alloy coated structural steel with guaranteed minimum yield strength of 300MPa with good ductility. Suitable for roll forming to a minimum internal diameter of 1t.

Typical Uses

Roofing, Cladding, General Manufactured Articles

Standard*

AS 1397

*Other standards (e. g. ASTM A 792M, ISO 9364, IS15961 etc.) and grades on specific agreement

Properties of Steel Base

Mechanical Properties	Guaranteed Minimum
Logitudinal Tensile	
Yield Strength, MPa	300
Tensile Strength, MPa	340
Elongation on 80 mm, %	18
Hardness, HR30T	50

Chemical Composition of Steel Base

Element	Guaranteed Max# (%)
Carbon (C)	0.30
Manganese (Mn)	1.60
Phosphorus (P)	0.10
Sulphur (S)	0.035

Values shown refer to relevant standard unless specifically agreed to
Other elements that are not harmful for the application may be present

Coating Class

Coating Class	Minimum Coating - Total Both Surfaces, g/m ²	
	Triple Spot Test	Single Spot Test
AZ150	150	135
AZ200	200	180

Coating Adhesion - 180° Bend Test

Coating Class	Guaranteed Minimum
AZ150 / AZ200	1t

Dimension Range & Tolerances (AS/NZS 1365)**

Range	Base Metal Thickness (mm)	
	Tolerance	
	Width ≤ 1200	Width > 1200
0.30 - 0.50	± 0.03	± 0.04
0.51 - 0.80	± 0.04	± 0.05
0.81 - 1.20	± 0.05	± 0.06
1.21 - 1.30	± 0.06	± 0.07

Range	Width (mm)	
	Tolerance	
< 900 (in slit edge)	+1 / - 0	
914 - 1000	+ 4 / - 0	
1001 - 1250	+ 5 / - 0	

**For requirements beyond the standard product range & tolerance, please contact Tata BlueScope Steel Office

Fire Hazard Properties (AS/NZS 1530.3)

Index	Range	Rating
Ignitability Index	0-20	0
Spread of Flame Index	0-10	0
Heat Evolved Index	0-10	0
Smoke Developed Index	0-10	0-1

Supply Conditions

Supply Condition	Normal	Optional
Surface Condition	Spangled	–
Coating Class	AZ150 ⁱ	AZ200 ⁱⁱ
Surface Treatment	Passivated and Resin coated	Passivated (for post painting/ paint line feed)
Branding	Branded	Unbranded
Tolerance Class ⁱⁱⁱ		
1. Dimensions	A Class	–
2. Flatness	A Class	–

i) Metallic coating of minimum 150 g/m², ii) Metallic coating of minimum 200 g/m², iii) Dimensional and shape tolerances as per AS/NZS 1365

Fabrication Performance

Method	Rating [#]	Method	Rating [#]
Drawing	2	Lock Seam Forming	5
Pressing	2	Welding	4
Bending	5	Painting with Pre-treatment	5
Roll-forming	5		

where 1 = limited to 5 = excellent, NR = not recommended

Material should be used promptly (within 6 months) to avoid the possibility of improper storage related corrosion & change in performance due to ageing

Typical Property Ranges (For Normal Supply Product)

Yield Strength (MPa)		
	Minimum	Maximum
0.35	330	400
0.45	320	390
0.75	315	385
1.0	310	375
1.2	300	370
Tensile Strength (MPa)		
0.35	410	460
0.45	400	450
0.75	395	440
1.0	385	430
1.2	375	420
Total Elongation on 80mm (%)		
0.35	18	28
0.45	20	30
0.75	23	31
1.0	25	32
1.2	25	32

Note:

©2015 Tata BlueScope Steel Ltd. All rights reserved. This brochure and its content is copyright of Tata BlueScope Steel Ltd. No part of this brochure may be reproduced or transmitted in any form or by any means, electronic or mechanical including photocopy, recording, or any information storage and retrieval system, without permission in writing from Tata BlueScope Steel Ltd.

ZINCALUME® steel is a registered trademark of BlueScope Steel Limited under license to Tata BlueScope Steel Limited.

Tata BlueScope Steel Ltd.

CIN : U45209PN2005PLC020270

Regd. Office: The Metropolitan, Final Plot No. 27,
Survey No. 21, Wakdewadi, Shivaji Nagar,
Pune - 411005. INDIA. Tel: +91 20 6621 8000

Website: www.tatabluescope-cs.com

Email: coatedsteel@tatabluescopesteel.com